

Micromachining for Terahertz Applications

Victor M. Lubecke, Koji Mizuno, and Gabriel M. Rebeiz.

V.M. Lubecke, K. Mizuno, Photodynamics Research Center,
The Institute of Physical and Chemical Research (RIKEN)
19-1399 Koeji, Nagamachi, Aoba-ku, Sendai 980, Japan.
Tel: 81-22-228-2124, FAX: 81-22-228-2128,
E-mails: victor@postman.riken.go.jp, koji@riec.tohoku.ac.jp

K.Mizuno is also with the Research Institute of Electrical Communication
Tohoku University
2-1-1 Katahira
Aoba-ku, Sendai 980-77, Japan

G.M. Rebeiz, Engineering and Computer Science, Radiation Laboratory,
University of Michigan, Ann Arbor, MI 48109-2122, USA
Tel: (313) 647-1793, FAX: (313) 647-2106, E-mail: rebeiz@eecs.umich.edu

Abstract-

An overview of recent progress in the research and development of micromachined antennas, transmission-lines, waveguides structures, and planar movable components for terahertz frequencies is presented. Micromachining is shown to provide a low cost alternative to conventional (and very expensive) machined-waveguide technology, resulting in antennas with excellent radiation patterns, low-loss tuners, and 3-D micromachined structures suitable for terahertz applications. Fabrication procedures for a variety of micromachined waveguide and planar structures are described here, along with measured terahertz performance. Applications of micromachining techniques for terahertz systems include focal-plane imaging arrays requiring a large number of elements, and low-cost receivers for commercial and industrial applications such as pollution monitoring.

Index Terms- Submillimeter wave, millimeter wave, terahertz, MEMS, micromachining.

I. INTRODUCTION

The submillimeter-wave frequency range is usually defined from 300 GHz to 3 THz, corresponding to wavelengths between 1 mm and 100 μm . Recently, this frequency range has been included in the terahertz spectrum, which roughly extends from 100 GHz (3mm) to 3 THz (100 μm). The primary application for terahertz technology has so far been terrestrial and astronomical remote sensing, where low-noise receivers are used to observe electromagnetic emissions resulting from physical and chemical processes in the atmosphere and in outer space. Some key molecules like the hydroxyl radical (OH), which plays a critical role in all stages of ozone destruction and serves to remove harmful gasses from the atmosphere, have significant emissions only at terahertz frequencies [1,2]. Other applications for terahertz technology involve imaging systems demonstrated at around 94 GHz, which can be used to penetrate zero-visibility weather conditions (opaque even to infrared imaging systems) for aircraft guidance and landing, or to identify plastic guns and explosives in non-invasive security and contraband detection systems [3]. These applications require sensitive receivers, particularly in the form of focal-plane imaging arrays which can cover large detection-areas with minimum scanning and integration times.

As the desired wavelengths of operation become increasingly small, so do the dimensions for two- and three-dimensional antennas, quasi-optical lenses and mirrors, transmission lines, and related components. This makes terahertz technology well suited to high-resolution focal-plane imaging applications requiring large numbers of elements, and practical-sized receiver systems for scientific, commercial, and industrial applications. Unfortunately, small dimensions make terahertz waveguide components difficult and costly to fabricate through conventional machining and assembly. Integrated circuit technology offers practical advantages for terahertz systems, but planar components are subject to deleterious substrate modes and other loss mechanisms which severely limit performance with increasing frequency of operation. Mechanical limitations imposed by waveguide dimensions and electronic limitations due to device parasitics, also make it difficult to implement adjustable tuning and performance optimization in terahertz circuits.

Fortunately, novel applications of various micromachining techniques which provide precise control of two- and three-dimensional structures at the 1-100 μm level, are demonstrating a practical means for producing a variety of high-performance terahertz front-end components. The application of micromachining technology to terahertz circuits was explored as early as 1979 [4], with the fabrication of a 2.5 THz, 40- μm wide by 400- μm long (3.5 λ), tapered dielectric-rod antenna, micromachined from a silicon substrate (Fig. 1). Micromachining technology not only allows for the extension of antennas and receiver front-end components to higher frequencies, but also allows higher levels of circuit integration and the realization of complicated networks and arrays. With the use of micromachining, it is possible to build a large number of terahertz receivers/sub-systems for imaging array applications at a relatively low cost, which is a major advantage over conventionally fabricated waveguide-based receivers.

This paper reviews various micromachining techniques used to produce high-performance terahertz circuits. Since front-end components are the most expensive and least reproducible components in a terahertz system, micromachining research efforts have concentrated on the development of miniature high-efficiency antennas, low-loss transmission-lines, and adjustable tuning structures. Terahertz micromachining technology can be broadly divided into three categories: 1) fabrication techniques which facilitate the frequency scaling of three-dimensional components from established waveguide designs,

2) techniques for suppressing substrate mode losses in planar integrated circuits by removing part, or all, of the dielectric around critical electromagnetic components, and 3) techniques for integrating adjustable micromechanical components for low-loss circuit tuning and optimization. These approaches are covered in detail in the following sections.

II. FREQUENCY SCALED THREE-DIMENSIONAL COMPONENTS

There are several examples of the application of micromachining technology to directly reproduce conventional three-dimensional waveguide and antenna components, for terahertz frequencies. Micromachining research has been directed at fabricating such structures through photolithography, laser milling, and mold replication, to allow the scaling of these designs to higher frequencies, the fabrication of arrays and other intricate systems, and economical mass production. Waveguides micromachined from silicon and a mixer block produced from a mold have demonstrated performance equal to that of conventionally machined components, at 255 GHz and 690 GHz, respectively. This section describes the various micromachining techniques used for such components, and measured results.

Silicon Waveguides

Micromachined waveguides can be economically batch-processed from common silicon wafers, with critical dimensions determined through photolithography, anisotropic etching, and wafer thickness. Such waveguides are well suited to scaling for use at higher frequencies, and also include internal membrane structures on which thin-film devices could be readily integrated [5] [6]. The concept is illustrated in Fig. 2 (a).

The process for fabricating miniature WR-4 ($a = 1092 \mu\text{m}$, $b = 546 \mu\text{m}$) silicon waveguides is shown in Fig.2 (b). A thick 2- μm layer of silicon nitride (Si_3N_4) is first applied to each side of a double-side-polished, 546- μm thick silicon wafer with $\langle 110 \rangle$ surface orientation, through low pressure chemical vapor deposition (LPCVD). The wafer thickness establishes one half of the total width of the WR-4 waveguide (one half of dimension a). Long rectangles are then defined on the back side of the wafer, through which openings are etched through the silicon nitride. The patterned silicon nitride layer acts as an etch mask, and potassium hydroxide (KOH) is used to anisotropically etch straight-walled channels completely through the silicon wafer [7]. Accurate alignment of the channel masks to the $\langle 111 \rangle$ crystal plane of the silicon wafer is required to produce the extremely smooth sidewalls, needed for minimizing high frequency losses. The width of the channel defines the height of the WR-4 waveguide (dimension b). Selective electroless nickel deposition is used to provide a thin base layer of metalization to the silicon walls of the waveguide structure, and the wafer is bonded to a metal carrier using photoresist. An additional 3- μm layer of gold is electroplated over the conducting surfaces to enhance performance. The silicon nitride membrane can then be patterned to support planar devices and tuning circuits, before assembly with the top part of the waveguide (an identical structure, with the silicon nitride membrane removed). The plane where the two waveguide halves meet is noncritical, since no RF currents are present at this interface in fundamental mode operation. A similar process has been used to fabricate WR-10 ($a = 2540 \mu\text{m}$, $b = 1270 \mu\text{m}$) waveguides.

Silicon-etched waveguides were mounted in conventionally-machined brass fixtures to allow connection to a standard-waveguide test system. Insertion loss measurements, S_{21} , for 25.4 mm sections of both WR-10 and WR-4 waveguides were made from 75-110 GHz, and 200-255 GHz, respectively. The average measured loss was about 0.04 dB per wavelength for the WR-10 guide, and 0.80 dB per wavelength for the WR-4 guides. The WR-4 results are shown in Fig.2 (c). Both results are comparable to that of commercially available conventionally-fabricated metal waveguides. While the fabrication of waveguides which include membranes has been demonstrated, devices have not yet been integrated.

Metal-Film Waveguides and Antennas

An alternative approach for micromachined waveguide fabrication has been demonstrated using photoresist as a form structure to produce thin-film metal guides with integrated horn antennas at either end. A simple arrangement of back-to-back slotted horn antennas with a length of waveguide between them, shown in Fig. 3 (a), has been fabricated, with performance demonstrated at 200 GHz [8].

The process for fabricating this structure is as follows. A thick 100- μm layer of photoresist is spun onto a metalized substrate, and photo-patterned to produce a form structure for the waveguide and horn antennas. The width of the demonstrated waveguide was 1300 μm , and the flared antenna was 3965 μm long, and 5100 μm wide at the maximum aperture. The form structure is covered by a thin layer of evaporated gold, followed by a thicker, and thus stronger, electroplated layer of gold. A layer of thin photoresist is sprayed over the structure, and patterned to allow etching of gold from the front of each slotted horn antenna. The resist is then stripped in acetone, leaving an air-filled guide with flared antenna openings at either end.

Antenna patterns for the circuit, shown in Fig. 3 (b), were both simulated and measured at 200 GHz, with good agreement. The beam radiated from the slotted horns at an angle of approximately 27° upwards from the horizontal plane of the substrate, with a 3 dB beamwidth of 31° in the vertical plane, and 23° in the horizontal plane. Guide losses and antenna efficiency have not yet been reported. While resist thickness limits the structure to a height which corresponds to about 1/8-height waveguide at 200 GHz, full-height waveguide could be implemented by scaling the design to higher frequencies (800 GHz). However, increasing the versatility of circuits made through this process requires the implementation of devices or other circuitry within the closed waveguide structure, which will require the development of additional technology [9].

Resin Waveguides with Silicon Antennas

Another method proposed for micromachined waveguides with integrated horn antennas combines both selective silicon etching and photosensitive resin techniques [10,11]. Silicon micromachining is used to form a pyramidal horn antenna, which gradually tapers in a broad-band transition to join a waveguide made from photo-patterned resin, as illustrated in Fig. 4 (a). Such technology can be used not only to fabricate mixer blocks and receiver arrays, but for other terahertz waveguide-based circuits like multipliers and bandpass filters as well. However, hybrid assembly of thin quartz substrates containing diodes, IF filters, and DC bias circuitry is still required, since the photosensitive resin is not readily compatible with existing membrane technology.

The fabrication technique has been demonstrated to produce a mixer block, shown in Fig. 4 (b), on a scale suitable for 585 GHz operation. First, a mask with a shallow flare angle is aligned to the crystal orientation of a silicon wafer, allowing a V-type groove to be etched with side-walls inclined at an angle of 54.7° to the wafer surface. A silicon dioxide (SiO_2) mask layer is used to define the pattern, and the etch is timed to yield a flat $\langle 100 \rangle$ surface at the bottom of the groove, resulting in the formation of one half of the desired pyramidal horn. The wafer surface is then coated with a very thick, 200- μm planarized layer of photosensitive resin (Epon SU-8, or similar) [12] which is subsequently photopatterned to form the vertical sidewalls of the adjoining waveguides. An additional layer of resin is used to form alignment pins to facilitate the assembly of the split-block design. The remaining resin is then heat-cured, and the entire wafer is metalized through sputtering and electroplating. The split design provides access for the hybrid installation of devices and associated embedding circuitry, and formation of the waveguides and horns is completed when two halves are combined. While electrical performance has not yet been demonstrated, simulations using HP-HFSS indicate that the pattern of the pyramidal horn antenna can be tailored by simple variations in the fabrication process.

The practical high aspect ratio characteristics of the photosensitive resin used in this example have also been applied for the formation of other terahertz components. Dichroic plates with perforations of complex shape and ten or hundred micron scale features, too small for conventional machining, have been fabricated using similar resin. Enhanced resolution and uniformity have been obtained using a substrate based mask, and applied to create the 4 cm-diameter, 500 μm -thick dual-polarization dichroic plate, with hundred micron scale holes designed to pass 640 GHz while blocking 240 GHz, shown in Fig. 4(c). Designs for other dichroic plates for use up to 1 THz have also been realized, and similar techniques have been employed to batch-produce non-contacting waveguide backshorts for frequencies up to 2.5 THz, as shown in Fig. 4(d) [13,14].

Alternative Techniques: Laser Micromachining and Resin Molding

In addition to the photolithographic techniques described, alternative machining techniques are also being developed for the fabrication of small-scale versions of conventional components.

Laser Micromachining: Computer-controlled laser milling of silicon has been used to fabricate corrugated feedhorns and other components suitable for submillimeter wave operation [15]. Unlike photolithographic micromachining, laser milling offers the advantage of unrestricted feature formation in the third dimension. It also allows for the fabrication of smaller features with improved tolerance over conventional milling, without mechanically induced material damage. The process consists of the use of an argon-ion laser to locally heat a portion of a silicon substrate, in a chlorine ambient environment. The molten silicon reacts with the chlorine to form volatile silicon chlorides, which are removed to form the desired features in the substrate.

The process has been used to produce corrugated feed horn antennas, suitable for 810 GHz and 2.0 THz operation. The antennas were made by etching one half of the structure in a substrate, and then assembling two halves to complete the structure. For the 810 GHz component, a laser spot size of 6 μm was used to produce 8- μm features, maintaining a shaving depth of approximately 1 μm and a rate of $10^5 \mu\text{m}^3/\text{s}$. For the 2.5 THz component,

shown in Fig. 5 (a), a laser spot size of 3 μm was used to produce 4- μm features, maintaining a shaving depth of 0.65 μm and a rate of $5 \times 10^4 \mu\text{m}^3/\text{s}$.

Additionally, a replication process was developed which allows multiple copies to be molded from a laser-milled master. After flouridating the milled surface of the master, it is filled with polydimethylsiloxane (PDMS) to form a mold. A low-viscosity polymer precursor is then flowed over the mold and cured to form the copy, and the mold is recovered to be used for further copies. The copy is sputter-coated with 0.3 μm of gold, and the two halves assembled using UV-curable epoxy. Nearly Gaussian antenna patterns were measured for a back-to-back feedhorn component, shown in Fig. 5 (c) and (d), at 2 THz.

Resin Molding: A separate effort has been made to develop inexpensive high-precision copies of conventionally fabricated terahertz structures, through the casting of polyurethane structures with a silicone-based mold formed from a master structure. The technique, illustrated in Fig. 6, is referred to as mastering, molding, and casting [11]. In this process a silicone mold is formed on a conventionally machined master, and then filled with polyurethane which is subsequently cured and removed. The polyurethane components are then coated with sputtered gold, and an additional few microns of gold is added through electroplating. This effort has produced an entire mixer block, and measurements at 690 GHz have shown that the copies work as well as machined metal versions of the same design [16].

III. MEMBRANE-BASED MICROMACHINED COMPONENTS

An alternative to direct submillimeter wave scaling of three-dimensional waveguide structures is the development of equivalent two-dimensional integrated circuit structures. The performance of integrated circuit antennas and transmission lines on high-dielectric constant substrates is severely limited by power radiation into substrate modes, an effect which increases as a function of both f^3 and $(\epsilon_r - 1)^2$, where ϵ_r is the relative dielectric constant for the substrate [17]. Planar components are also subject to dielectric losses, which increase with frequency and can be prohibitively high for terahertz applications. One way to solve these problems is to integrate the antennas and transmission lines on very thin dielectric membranes (effectively making $\epsilon_r = 1$). The membranes can be made very thin, compared to a free-space wavelength, so that the antennas effectively radiate in free-space. This technique eliminates dielectric and substrate mode losses, and the design can be easily scaled to different frequencies.

The fabrication of membrane-based components proceeds as follows: A 1-1.4 μm -thick 3-layer structure of $\text{SiO}_2/\text{Si}_3\text{N}_4/\text{SiO}_2$ is deposited on a high-resistivity silicon substrate using thermal oxidation and LPCVD techniques. The layer must be in tension, resulting in flat and rigid membranes. The planar components (antennas, transmission lines, etc.) are patterned using standard photolithography. Next, an opening is defined on the back side of the wafer, underneath specific components through the use of an infrared aligner, and the silicon substrate is etched until the transparent dielectric membrane appears. The etchant used with silicon wafers is KOH or ethylene diamine pyrocatechol (EDP) [7], and both solutions result in a very low undercut rate and smooth sidewalls. The sidewalls form an angle of 54.7° with the planar top/bottom surfaces when a $\langle 100 \rangle$ silicon wafer is

used. Via holes, if needed, are etched at the same time as the membranes are formed, and are electroplated with gold.

Integrated Horn Antennas and Imaging Arrays

Perhaps the most intricate membrane-type antenna is the integrated horn antenna. In this design, a dipole probe is suspended on a dielectric membrane in a pyramidal cavity etched in silicon [18]. The horn collects incident energy and focuses it to the probe antenna on the membrane. A Schottky-diode or a planar superconductor-insulator-superconductor (SIS) detector is typically integrated at the apex of the dipole, and the signal is taken out with a simple low-pass filter. The integrated horn array is composed of two or more stacked silicon wafers with a $\langle 100 \rangle$ crystal orientation. The horn cavity is made by anisotropic etching of the silicon wafers, which produces a horn flare-angle of 70.6° . The opening of the front wafer determines the horn aperture size, 1.5λ , while the thickness of the front wafer(s) determines the position of the dipole antenna inside the horn (0.38λ from the apex of the horn). The wafer stack (front and back wafers) is aligned and assembled together to form the integrated horn cavity, and the horn walls are coated with gold to reduce RF losses. An advantage of this approach is that the dipole/detector structures occupy an area which is much smaller than a unit cell in an array, leaving space for additional RF, IF, and DC electronics. A 16×16 element “CCD-like” imaging array with 1.4λ -apertures has been demonstrated at 802 GHz [19]. At this frequency, the array period is $500 \mu\text{m}$ yielding total array dimensions of $8 \times 8 \text{ mm}$. The directivity of each antenna is 12 dB, which matches well with $f/0.75$ imaging system.

Integrated horn antennas can be designed to result in high antenna gains (up to 25 dB with metallic extensions) and very high Gaussian coupling efficiencies (more than 97%) (Fig. 7). Schottky-diode heterodyne receivers based on this antenna have all resulted in state-of-the-art antenna patterns and receiver DSB performances (5.5 dB DSB at 94 GHz, 7.2 dB at 250 GHz, and 8.4 dB at 350 GHz), with practical 15-20% bandwidths [20-23]. In this case, the planar Schottky-diodes were placed at the apex of the dipole on the Si_3N_4 membrane using hybrid techniques, and silver epoxy was used to establish an electrical contact between the integrated dipole antenna and the Schottky-diode. This arrangement has been tested by NASA and by Aerojet Corp., and survived satellite-launch temperature and vibration tests. Recently, a 3×3 imaging array of micromachined horn antennas with thin-film SIS detectors and integrated tuning elements on silicon-nitride membranes was demonstrated with excellent antenna patterns and receiver DSB performance (30 K at 106 GHz and 50 K at 190 GHz, with the receiver cooled to 4.2 K), again with a practical 10-15% bandwidth [24-26]. The 3×3 micromachined array allows the use of a backing magnet behind the antennas without interfering with the radiation patterns (necessary for proper operation of the SIS detectors), and allows ample space for the extraction of nine IF signals with high IF bandwidths.

Other Membrane-Type Antenna, Bolometer, SIS Detector, and Transmission Line Structures

The membrane type approach has also been applied to other antenna designs. A 100-800 GHz log-periodic antenna was integrated on a membrane and backed by an absorbing cavity [27]. A micromachined corner cube with a traveling-wave antenna on a membrane was developed for 2.5 THz applications and resulted in 18-19 dB gain [28]. This type of antenna is particularly well-suited for Schottky-diode detectors since the feed

of the traveling-wave antenna is at the silicon (or GaAs)-membrane interface. A double-dipole antenna integrated on a membrane and backed by a ground plane was used as a feed for a small parabolic reflector (5 mm diameter) and resulted in a directivity of 37 dB at 2.5 THz [29]. This antenna is well suited for SIS detectors or hot-electron bolometers at 800 GHz and above. Also, a broken linearly tapered slot antenna (BLTSA) on a thin dielectric membrane was developed for use at 350 GHz and 802 GHz, and resulted in symmetrical patterns with a 10-dB beam-width of 44° [30]. The BLTSA has been used at 500 GHz with a hot-electron bolometer detector and provided good radiation patterns and receiver performance [31].

Another application of dielectric membranes is in bolometric detectors. The membrane provides heat isolation from the substrate and therefore results in bolometers with high responsivity and low noise-equivalent-power (NEP) [32,33]. A large area bismuth bolometer was developed on a membrane as a power-density sensor for terahertz frequencies, and operated successfully from 100 GHz to 10 THz. The 1 μm membrane is electrically thin even at 10 THz, and therefore does not affect the bolometer bandwidth. The bolometer performance was limited by 1/f noise, and a minimum power density of around 100 nW/cm² could be detected. Still, easy calibration of absolute power at terahertz frequencies was possible. Bolometric-type detectors have also been used with integrated horn antennas and have achieved a record room-temperature NEP of 8.3x10⁻¹¹ W/Hz^{1/2}, measured at 1 KHz chopping frequency [34].

A thin membrane "window" has also been recently demonstrated, inside an 850 GHz SIS waveguide receiver. In a typical configuration, an SIS detector is integrated on a thin quartz wafer. However, the required thickness of the wafer and the dimensions of the channel that hold the junction become too small at high frequencies for practical fabrication and assembly. In this application, the SIS device was integrated on a 1-μm membrane, which while electrically thin could provide adequate support from the surrounding silicon wafer. The resulting receiver showed an uncorrected receiver noise temperature of 514 K at 800-840 GHz when the mixer was cooled to 4.2 K [35].

Dielectric membranes have also been used to support terahertz transmission lines and filters. The loss for a membrane-supported coplanar strip transmission line (CPS) (20 μm strip width, and 20 μm separation) was measured from 100 GHz to 1 THz using electro-optic techniques, and was less than 0.1 Np/mm at 1 THz, compared to 1.5 Np/mm for the same line on GaAs [36]. One very practical micromachined transmission line topology is a type of shielded coplanar-waveguide called microshield line. Microshield line was utilized to fabricate the first planar bandpass filter at 250 GHz [37]. The bandpass filter has a relative bandwidth of 58 % and utilizes four quarter-wavelength open-end series stubs, as shown in Fig. 8 (a). The filter is 1 mm long, which is around 0.8 λ_g, at 250 GHz, where λ_g is the effective guided wavelength for the transmission line. The microshield filter is contained in a cavity, with dimensions given in Fig. 7(b), and the dominant waveguide mode cut-off frequency for this structure is greater than 500 GHz. The measured results for this filter in Fig. 8 (c) show a 1.0-1.5 dB pass-band insertion loss and excellent stop-band rejection. This, and the preceding examples demonstrate the significant performance benefits available through the simple micromachining of membrane structures.

IV. MICROMECHANICALLY ADJUSTABLE COMPONENTS

Micromachining techniques have also been used to provide integrated adjustable components which add the benefit of post-fabrication tuning and performance optimization to terahertz circuits. These *moving* components provide conventional mechanical circuit adjustments, yet have structures which are uniquely suited to photolithographic fabrication, planar circuitry, and micromanipulation.

The first (and only) micromechanically adjustable component demonstrated at submillimeter frequencies is the sliding planar backshort (SPB). It was developed to provide continuously adjustable tuning, like that of waveguide backshorts, to terahertz integrated circuits. An SPB tuner, illustrated in Fig. 9 (a), consists of a movable, patterned metal plate which is fabricated as an integrated part of a coplanar transmission line. The pattern is designed to form a selective broad-band RF short circuit on the transmission line beneath it, and can be arbitrarily positioned along the line to vary the electrical length. The reflection coefficient, S_{11} , was measured at -0.02 dB for a 2 GHz CPW model, and -0.3 dB for a 2 GHz CPS model, which was consistent with circuit measurements at 620 GHz [38], and 100 GHz [39], respectively.

The entire micromechanical SPB tuning structure is fabricated through micromachining techniques developed to be compatible with those commonly for terahertz integrated circuits [40]. The procedure for fabricating a 620 GHz SPB is illustrated in Fig. 9 (b). A coplanar transmission line is first (sputter) coated with a thin dielectric layer (SiO_2), and then covered with a sacrificial patch of thin-film metal (Cu), deposited and photo-patterned over the region where the SPB will be positioned. A thick 8- μm layer of photoresist is deposited over this metal, and patterned to allow the 5- μm thick SPB plate structure to be formed through electroplating (Au). The resist is stripped, and the entire metal structure is electroplated with about 1 μm of sacrificial metal (Cu). A thick 10- μm layer of polyimide is deposited and photo-patterned to form strips which anchor to the substrate, and partially overlap the edges of the two sides of the metal structure. Finally, all of the sacrificial metal is etched away, releasing the SPB plate to move freely along the length of the line, within the confines of the polyimide guide strips. The SPB plate structure is 200 μm wide, about 5 μm thick, and consists of five or more covered/uncovered sections, each roughly $g/4$ long. On an SiO_2 substrate ($g = 312 \mu\text{m}$), covered sections are 80 μm long, and uncovered sections are 65 μm and 75 μm long.

The performance of two mechanically manipulated SPB tuners has been successfully demonstrated in a 620 GHz quasi-optical monolithic integrated circuit, varying the power delivered from a planar antenna to a thin-film thermal detector over a range of nearly 15 dB. The circuit used a dielectric-filled parabola [41] to focus radiation onto a slot antenna, and coupled this radiation to a bismuth detector by means of two CPW transmission lines (with 8 μm gaps and a 16 μm -wide center conductor), each with integrated SPB tuners. One SPB was used to create a variable series reactance between the antenna and the detector, potentially serving to compensate for any off-resonance reactance of the slot. The other SPB created a variable susceptance in parallel with the detector, and could act to compensate for the parasitic capacitance found in some common submillimeter wave devices. An SEM photograph of the circuit is shown in Fig. 10 (a), and the normalized power delivered to the detector, P_n , is shown in Fig. 10 (b) as a function of the position of the series tuning element, l_s , for a fixed position of the parallel tuning element.

This versatile sliding structure can be readily implemented in a wide range of terahertz integrated circuits, to serve as transmission line tuners, antenna elements, shutters, and other adjustable components. The monolithic design of the SPB makes it suitable for

scaling to several terahertz, where the aspect ratio of the tuner is actually more suitable for conventional photolithographic thin-film techniques. However, the smaller structure and shorter wavelength would make it more difficult to manipulate the tuner externally, and thus some form of integral electromechanical actuation would be desirable. Electrostatic techniques [42] and thin-film shape-memory alloys [43] offer promise for this function.

CONCLUSION

This paper summarizes recent micromachining research efforts for terahertz applications. A large part of this work has been directed at the development of antennas and front-end components, which can be integrated in large numbers for focal-plane arrays or low-cost terahertz systems. Waveguide antennas, transmission lines, and mixer block assemblies have been fabricated through various economical micromachining techniques, with performance comparable to that of costly conventionally produced components. Practical techniques have also been developed to improve the performance of terahertz integrated circuits, through substrate removal and the integration of adjustable micromechanical tuning elements. These approaches offer great potential for the production of intricate terahertz systems, which can serve to advance the state-of-the-art in space and atmospheric research, and to extend the use of the terahertz spectrum to broader industrial and commercial applications.

REFERENCES

- [1] J.W. Waters, "Submillimeter-Wavelength Heterodyne Spectroscopy and Remote Sensing of the Upper Atmosphere," *Proceedings of the IEEE*, vol. 80, no. 11, pp. 1679-1701, November 1992.
- [2] T.G. Phillips and J. Kreene, "Submillimeter Astronomy," *Proceedings of the IEEE*, vol. 80, no. 11, pp. 1662-1678, November 1992.
- [3] P.F. Goldsmith, C.-T. Hsieh, G.R. Huguenin, J. Kapitzky, and E.L. Moore, "Focal Plane Imaging Systems for Millimeter Wavelengths," *IEEE Trans. Microwave Theory and Tech.*, vol. 41, no. 10, pp.1664-1675, October 1993.
- [4] D.B. Rutledge, S.E. Schwarz, T.L. Hwang, D.J. Angelakos, K.K. Mei, and S. Yokota, "Antennas and Waveguides for Far-Infrared Integrated Circuits," *IEEE Journal of Quantum Electronics*, vol. 16, pp. 508-516, May 1980.
- [5] W.R. McGrath, C.K. Walker, M. Yap, and Y.-C. Tai, "Silicon Micromachined Waveguides for Millimeter-wave and Submillimeter-wave Frequencies," *IEEE Microwave and Guided Wave Letters*, vol. 3, pp. 61-63, 1993.
- [6] J. A. Wright, S. Tatic-Lucic, Y.-C. Tai, W.R. McGrath, B. Bumble, H. LeDuc, "Integrated Silicon Micromachined Waveguide Circuits for Submillimeter Wave Applications," *Sixth International Symposium on Space Terahertz Technology*, Pasadena, CA, pp. 387-396, March 1995.
- [7] K.E. Peterson, "Silicon as a Mechanical Material," *Proceedings of the IEEE*, vol. 70, no.5, May 1982.
- [8] J. W. Digby, C.E. Collins, B.M. Towlson, et al., "Integrated Micro-Machined Antenna for 200 GHz Operation," *IEEE MTT-S International Microwave Symposium*, pp. 561-564 June 1997.
- [9] C.M. Mann, J.L. Hesler, P.J. Koh, T.W. Crowe, W.L. Bishop, R.M. Weikle, and D.N. Matheson, "A Versatile Micromachined Horn Antenna," *20TH ESTEC Antenna Workshop on Millimetre Wave Antenna Technology and Antenna Measurements*, Noordwig, June,1997.
- [10]T.W. Crowe, P. J. Koh, W.L. Bishop, C. M. Mann, et al., "Inexpensive Receiver Components for Millimeter Wavelengths," *Eighth International Symposium on Space Terahertz Technology*, pp. 377-384 March 1997.
- [11]S.T.G. Wootton, S.R. Davies, N.J. Cronin, "a Novel Micromachined 1.6 THz Mixer," *Twenty Second International Conference on Infrared and Millimeter Waves*, pp. 132-133, July 1997.
- [12]K.Y. Lee, N. LaBianca, S.A. Rishton, et al., "Micromachining Applications of a High Resolution Ultrathick Photoresist," *J. Vac. Sci. Technol. B* 13(6), pp. 3012-3016, Nov/Dec 1995.
- [13]V.M. Lubecke, C. M. Mann, and K. Mizuno, "Practical Micromachining Techniques for High Aspect Ratio Submillimeter Wave Components," *Ninth International Symposium on Space Terahertz Technology*, Pasadena, CA, March 1998.

- [14]V.M. Lubecke, T. Hamano, C. M. Mann, and K. Mizuno, "Micromachining of Photo-Plastic Submillimeter Wave Components," Proceedings of the *Asia-Pacific Microwave Conference*, Yokohama, Japan, December 1998.
- [15]C.K. Walker, G. Narayanan, H. Knoephle, et al., "Laser Micromachining of Silicon: a New Technique for Fabricating High Quality Terahertz Waveguide Components," *Eighth International Symposium on Space Terahertz Technology*, pp. 358-376, March 1997.
- [16]T. Crowe, private communication, February 1998.
- [17]D.B. Rutledge, S.E. Schwarz, and A.T. Adams, "Infrared and submillimetre antennas," *Infrared Physics*, vol. 18, pp. 713-729, 1978.
- [18] G.M. Rebeiz, D.P. Kasilingam, Y. Guo, P.A. Stimpson, and D.B. Rutledge, "Monolithic millimeter-wave two-dimensional horn imaging arrays," *IEEE Trans. Antennas Propagat.*, vol. AP-38, pp. 1473-1482, Sept. 1990.
- [19]W.Y. Ali-Ahmad and G.M. Rebeiz, Gordon Chin and Hermant Davee, "802 GHz integrated horn antennas imaging array," *Int. J. Infrared Millimeter Waves*, vol. 12, pp. 481-486, May 1991.
- [20]G.V. Eleftheriades and G.M. Rebeiz, "Analysis and design of millimeter-wave quasi-integrated horn antennas," *IEEE Trans. Microwave Theory and Tech.*, vol. MTT-41, pp. 54-965, June/July 1993.
- [21]W.Y. Ali-Ahmad, and G.M. Rebeiz, "An 86-106 GHz quasi-integrated low-noise receiver," *IEEE Trans. Microwave Theory Tech.*, vol. MTT-41, No. 4, pp. 558-564, Apr. 1993.
- [22]W.Y. Ali-Ahmad, W.L. Bishop, T.W. Crowe and G.M. Rebeiz, "250 GHz quasi-integrated low-noise Schottky-receiver," *Int. J. Infrared Millimeter Waves*, vol. 14, pp. 737-748, Apr. 1993.
- [23]W.Y. Ali-Ahmad and G.M. Rebeiz, "A 335 GHz integrated Schottky receiver," *IEEE Microwave Guided Wave Lett.*, vol. MGWL-4, pp. 37-39, Feb. 1994.
- [24]Garcia, E., B. R. Jacobson, and Qing Hu, "Fabrication of high-quality SIS junctions on thin SiN membranes," *Appl. Phys. Lett.* 63, 1002, (1993).
- [25]de Lange, G., B. R. Jacobson, and Q. Hu, "A low-noise micromachined millimeter-wave heterodyne mixer with Nb superconducting tunnel junctions," *Appl. Phys. Lett.* 68, 1862 (1996).
- [26]de Lange, A. Rahman, E. Duerr, and Q. Hu, "Low-noise Micromachined SIS Mixers for Millimeter-wave Imaging Arrays," *IEEE Trans. on Appl. Superc.* 7, 3593 (1997).
- [27]G.M. Rebeiz, W. Regehr and D.B. Rutledge, R.L. Savage and N.C. Luhmann, Jr. "Submillimeter-wave antennas on thin membranes," *Int. J. Infrared Millimeter Waves*, vol. 8, pp. 1249-1256, Oct. 1987.

- [28] S.S. Gearhart, C.C. Ling and G.M. Rebeiz, H. Davee and G. Chin, "Integrated 119 μm linear corner-cube array," *IEEE Microwave Guided Wave Lett.*, vol. MGWL-1, pp. 155-157, July, 1991.
- [29] D.F. Filipovic, W.A. Ali-Ahmad and G.M. Rebeiz, "Millimeter-Wave Double-Dipole Antennas for High-Gain Integrated Reflector Illumination," *IEEE Trans. Microwave Theory Tech.* vol. MTT-40, pp. 962-967, May 1992.
- [30] P.R. Acharya, H. Ekstrom, S.S. Gearhart, J.F. Johansson, S. Jacobson, G. M. Rebeiz and E.L. Kollberg, "Tapered slotline antennas at 802 GHz," *IEEE Trans. Microwave Theory Tech. Special Issue on Quasi-Optical Techniques*, vol. MTT-41, pp. 1715-1719, Oct. 1993.
- [31] Y. P. Goussev et al., "Quasi-optical superconducting hot electron bolometer for submillimeter-waves," *J. Infrared and Millimeter-Waves*, vol. 17, No.2, pp. 317-331, 1996.
- [32] C.C. Ling and G.M. Rebeiz, "A wideband monolithic quasi-optical power meter for millimeter-wave and submillimeter-wave applications," *IEEE Trans. Microwave Theory Tech.*, vol. MTT-39, pp. 1257-1261, Aug. 1991.
- [33] C.C. Ling, J.C. Landry, H. Davee, G. Chin and G.M. Rebeiz, "Large area bolometers for THz power measurements," *IEEE Trans. Microwave Theory Tech.*, vol. MTT-42, pp. 758-760, Apr. 1994.
- [34] Rahman, A., G. de Lange, and Q. Hu, "Micromachined room-temperature microbolometers for millimeter-wave detection," *Appl. Phys. Lett.* 68, 2020 (1996).
- [35] J.W. Kooi, J. Pety, B. Bumble, C.K. Walker, H.G. LeDuc, P.L. Schaffer and T.G. Phillips, "An 850 GHz waveguide receiver employing a niobium SIS junction fabricated on a 1- μm Si_3N_4 membrane," *IEEE Trans. Microwave Theory Tech.*, vol. 46, pp. 151-161, Feb. 1998.
- [36] H.J. Cheng, J.F. Whitakker, T.M. Weller and L.P. Katehi, "Terahertz-bandwidth characteristics of coplanar transmission-lines on low permittivity substrates," *IEEE Trans. Microwave Theory Tech.*, vol. 42, pp. 2399-2406, Dec. 1994.
- [37] T.M. Weller, L.P. Katehi and G.M. Rebeiz, "A 250 GHz microshield band-pass filter," *IEEE Microwave Guided Wave Lett.*, vol. MGWL-5, pp. 153-155, May 1995.
- [38] V.M. Lubecke, W.R. McGrath, P.A. Stimson, and D.B. Rutledge, "Micromechanical Tuning Elements in a 620 GHz Integrated Circuit," accepted for the *IEEE Transactions on Microwave Theory and Techniques*, submitted December 1997.
- [39] V.M. Lubecke, W.R. McGrath, and D.B. Rutledge, "A 100 GHz Coplanar Strip Circuit Tuned with a Sliding Planar Backshort," *IEEE Microwave and Guided Wave Letters*, vol. 3, no. 12, pp. 441-443, December 1993.
- [40] V.M. Lubecke, W.R. McGrath, Y-C. Tai, and D.B. Rutledge, "Microfabrication of Linear Translator Tuning Elements in Submillimeter Wave Integrated Circuits," accepted for the *IEEE/ASME Journal of Microelectromechanical Systems*, submitted December 1997.

- [41]P.H. Siegel and R.J. Dengler, "The Dielectric-Filled Parabola: A New Millimeter and Submillimeter Wavelength Receiver/Transmitter Front End," *IEEE Transactions on Antennas and Propagation*, vol. 39, no. 1, pp. 40-47, January 1991.
- [42]T.Akiyama and K. Shono, "Controlled Stepwise Motion in Polysilicon Microstructures," *IEEE/ASME Journal of Microelectromechanical Systems*, vol. 2, no. 3, pp. 106-110, September 1993.
- [43]P. Krulevitch, A. P. Lee, P.B. Ramsey, J.C. Trevino, J. Hamilton, and M.A. Northrup, "Thin Film Shape Memory Alloy Microactuators," *IEEE/ASME Journal of Microelectromechanical Systems*, vol. 5, no. 4, pp. 270-282, December 1996.

FIGURE CAPTIONS:

Fig. 1: Diagram of a 2.5 THz silicon dielectric-waveguide antenna with a membrane-supported bismuth bolometer load. A pioneering effort employed silicon micromachining to produce a 400- μm long (3.5 λ) by 40- μm wide tapered-rod antenna with a well-defined directional beam [4].

Fig. 2: Concept (a), fabrication overview (b), and measured performance (c) of silicon micromachined waveguides. Photolithography, anisotropic etching, and electro/electroless plating have been used to batch process split-waveguide halves with integrated membranes (accessible for device integration), with measured insertion loss, S_{21} , for the assembled waveguides (WR-4 : $a = 1092 \mu\text{m}$, $b = 546 \mu\text{m}$) comparable to that of conventionally produced commercial waveguide [6].

Fig. 3: Photograph (a) and radiation patterns (b) for a circuit consisting of a metal-film waveguide with integrated flared-horn antennas, fabricated through photoresist forming techniques. The closed 1/8-height 200 GHz waveguide has cross section dimensions of 80 μm by 1300 μm , and measured vertical plane, Theta, and horizontal plane (at 27 $^\circ$), Phi, radiation patterns agree with theory [8].

Fig. 4: Concept (a) and SEM photograph (b) of a mixer block designed for 585 GHz, fabricated through silicon and thick photosensitive resin micromachining techniques [10,11], and SEM photographs of a high aspect ratio dual-polarization dichroic plate for 640 GHz (c) and non-contacting waveguide backshort for 2.5 THz (d), also fabricated with thick photosensitive resin [13, 14]. The waveguide channels in the mixer block are 200 μm by 400 μm , the crossed vertical-walled rectangular apertures for the 500- μm thick dichroic plate are each about 400 μm by 100 μm , and the tip of the backshort has dimensions of about 30 μm by 90 μm .

Fig. 5: SEM photographs of a 2 THz corrugated feedhorn milled from silicon with a laser (a), back-to-back feed horns replicated with a mold process (b), and measured radiation patterns for the latter. A 3- μm laser spot size was used to mill the original terahertz structure, and measured orthogonal radiation patterns, θ and ϕ , for the mold-produced structure are Gaussian [15].

Fig. 6: Molding, and casting technique used to replicate inexpensive copies of terahertz component from a master [11]. Smooth waveguide features on the order of hundreds of microns have been accurately reproduced, and measured performance for a mold produced mixer block at 690 GHz are the same as that for a conventionally machined version.

Fig. 7: SEM photograph of a micromachined horn antenna (a), the geometry of a 350 GHz integrated horn receiver with an extension section for improved Gaussian-coupling efficiency with $s = 0.085$, $a_s = 1.35$, $\theta_0 = 8.5$ degrees, $L_M = 13 \lambda$, $X_N = 5.4 \lambda$ (b), the cross-section of the antenna showing the location of the membrane (and the dipole/diode) (c), and the measured patterns at 370 GHz with a comparison with theory (d). The Gaussian coupling efficiency is 97% [20].

Fig. 8: Metalization pattern for the four-section microshield bandpass filter (a) (not to scale), cross-sectional view (b), and comparison between measured and simulated results

at 150-350 GHz (c) [37]. Dimensions are: $L = 250 \mu\text{m}$, $S = 50 \mu\text{m}$, $W = 10 \mu\text{m}$, $H = 200 \mu\text{m}$, $W_1 = 320 \mu\text{m}$, and $W_2 = 40 \mu\text{m}$.

Fig. 9: Concept (a) and fabrication overview (b) for an integrated sliding planar backshort demonstrated at 620 GHz. Micromachining techniques made compatible with terahertz integrated circuit technology, are used to form a guide-restricted metal pattern ($200 \mu\text{m}$ wide, $5 \mu\text{m}$ thick) which slides over a dielectric-coated coplanar transmission line to vary the electrical length [40].

Fig. 10: SEM photograph (a) and measured performance (b) for a quasi-optical 620 GHz monolithic detection circuit with two integrated sliding planar backshort tuners. The two tuners consist of five high/low impedance sections (each $70 \mu\text{m}$ to $80 \mu\text{m}$ long), and are integrated with CPW transmission lines ($16\text{-}\mu\text{m}$ wide center conductor, $8\text{-}\mu\text{m}$ gaps), as series and parallel tuners used to vary the power delivered from a slot antenna to a bismuth detector over a range of nearly 15 dB. The normalized detected power, P_n , is shown as a function of the series tuning element position, l_s , for a fixed position of the parallel tuning element [38].